

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Previously Amended) An R-T-B based sintered magnet having a composition comprising:

27.0 mass% to 32.0 mass% of R, which is at least one of Nd, Pr, Dy and Tb and which always includes either Nd or Pr;

63.0 mass% to 72.5 mass% of T, which always includes Fe and up to 50% of which is replaceable with Co;

0.01 mass% to 0.08 mass% of Ga; and

0.85 mass% to 0.96 mass % of B,

wherein the magnet comprises a main phase with a tetragonal $R_2T_{14}B$ type crystal structure, which accounts for at least 90% of the overall volume of the magnet, but includes substantially no $R_{1.1}Fe_4B_4$ phases.

2. (Original) The R-T-B based sintered magnet of claim 1, further comprising at most 2.0 mass% of M, which is at least one element selected from the group consisting of Al, Si, Ti, V, Cr, Mn, Ni, Cu, Zn, Zr, Nb, Mo, In, Sn, Hf, Ta and W.

3. (Canceled)

4. (Original) The R-T-B based sintered magnet of claim 1 or 2, having an oxygen concentration of at most 0.5 mass%, a nitrogen concentration of at most 0.2 mass%, and a hydrogen concentration of at most 0.01 mass%.

5. (Currently Amended) A method for producing an R-T-B based sintered magnet, the method comprising the steps of:

preparing a powder ~~of an alloy that has a~~ composition comprising 27.0 mass% to 32.0 mass% of R (which is at least one of Nd, Pr, Dy and Tb and which always includes either Nd or Pr), 63.0 mass% to 72.5 mass% of T (which always includes Fe and up to 50% of which is replaceable with Co), 0.01 mass% to 0.08 mass% of Ga and 0.85 mass% to 0.96 mass % of B of an alloy;

compacting and sintering the alloy powder, thereby making a sintered magnet; and
subjecting the sintered magnet to a single heat treatment at a temperature of 400°C to 600°C.

6. (Original) The method of claim 5, wherein the step of preparing the alloy powder includes the steps of:

preparing a melt of the alloy;
rapidly cooling and solidifying the melt of the alloy by a strip casting process, thereby making a rapidly solidified alloy; and
pulverizing the rapidly solidified alloy.

7. (New) A method for producing an R-T-B based sintered magnet, the method consisting essentially of:

preparing a powder composition comprising 27.0 mass% to 32.0 mass% of R (which is at least one of Nd, Pr, Dy and Tb and which always includes either Nd or Pr), 63.0 mass% to 72.5 mass% of T (which always includes Fe and up to 50% of which is replaceable with

Co), 0.01 mass% to 0.08 mass% of Ga and 0.85 mass% to 0.96 mass % of B of an alloy;
compacting and sintering the alloy powder, thereby making a sintered magnet; and
subjecting the sintered magnet to a heat treatment at a temperature of 400°C to 600°C.